

ESPECIFICACIONES DE ACABADO FINISH SPECIFICATIONS

HOLO AMETHYST OCHRE BLUE

Espesor de pintura EN 13523-1	30-57µ (*) (-6µ / +6µ) 70% Kynar 500
Brillo especular EN 13523-2	(*) Dependiendo del color específico Brillo medido a 60° Gardner: 20-35 g.u. (tolerancias según la NORMA EN 1396, tabla 4)
Dureza, método del lápiz EN 13523-4	≥ F
Adherencia EN 13523-5	Resistencia al impacto medido en 7,5 [Nm/mm] SIN GRIETAS
Adherencia & Impacto EN 13523-6	Pérdida de adhesión ≤ GT1 (más del 95% permanece en la superficie)
T-Bend EN 13523-7	Doblado a 180° sobre muestra plana en temple H44 Mínimo T ≥ 1,5 (doblado 4 veces) SIN GRIETAS
Resistencia a la niebla salina EN 13523-8	1000 horas de ensayo Clase 2 (según la NORMA EN 1396, tabla C4)
QV-B Test EN 13523-10	1000 horas de ensayo (500h de QV-B) Ligeros cambios de color y pérdida de brillo ≤ 10%
Resistencia MEK EN 13523-11	≤ 100 pasadas dobles
Resistencia a la humedad ASTM D2247-68	Después de 1000 horas de ensayo SIN INFLUENCIA

HOLO AMETHYST OCHRE BLUE

Coating thickness EN 13523-1	30-57µ (*) (-6µ / +6µ) 70% Kynar 500
Specular gloss topcoat EN 13523-2	(*) Depending on specific colour Gloss measured by 60° Gardner: 20-35 g.u. (tolerances according NORM EN 1396, table 4)
Pencil hardness EN 13523-4	≥ F
Adhesion to cracking on rapid deformation EN 13523-5	Reverse impact resistance measures by 7,5 [Nm/mm] NO CRACKS
Adhesion to cracking on rapid deformation after indentation EN 13523-6	Loss of adhesion ≤ GT1 (more than 95% remains on the surface)
Resistance to cracking on bending EN 13523-7	Bending through 180° on flat material up to temper H44 Minimum T ≥ 1,5 (bending 4 times) NO CRACKS
Resistance to salt acid spray fog EN 13523-8	After 1000 hours testing Corrosion index 2 (according NORM EN 1396, table C4)
QV-B Test EN 13523-10	After 1000 test hours (500 hours UV-B test) Slight color change allowed and Gloss reduction ≤ 10%
M.E.K / Solvent rubbing test EN 13523-11	≤ 100 double rubs
Humidity resistance ASTM D2247-68	After 1000 hours testing NO INFLUENCE